



TIKKURILA

## SUPI SAUNAVAHA

PROTECTIVE WOODWAX FOR SAUNA

### DESCRIPTION

Protective agent for interior wooden surfaces, contains natural wax.

### RECOMMENDED USES

For sauna benches, paneled walls and ceilings, doors and window frames.

### PRODUCT FEATURES

A surface treatment for wooden surfaces in saunas. The wax is absorbed into the wood, forming a natural barrier to dirt and water.



The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

# SUPI SAUNAVAHA

## TECHNICAL DATA

<b>Base paints</b>	EP BASE
<b>Colour Shades</b>	<b>Color cards:</b> Interior wood stains and lacquers. Can be tinted in Tikkurila translucent colors. Standard colors Black, White and Gray
<b>Coverage</b>	10–13 m <sup>2</sup> /l, depending on the species of wood.
<b>Can sizes</b>	EP BASE: 0.225 l, 0.9 l, 2.7 l FACTORY READYMADE SHADE: 0.333 l, 1 l, 3 l
<b>Application method</b>	Apply with a foam brush, sponge or brush with artificial bristles.
<b>Drying time (23°C and 50% relative air humidity)</b>	Dust-dry in approx. 30 minutes to 1 hour. Ready for use after 24 hours.
<b>Density (kg/l)</b>	1.0 kg/l, ISO 2811.
<b>Volume solids (%)</b>	24
<b>Storage</b>	Protect from frost. Protect from frost

# SUPI SAUNAVAHA

## APPLICATION INSTRUCTIONS

### Application conditions

The surface to be treated must be dry, the ambient temperature at least +5 °C and the relative humidity of air below 80%.

### Surface preparation

New clean wood surfaces:

Clean the wood surface of any dirt and dust. Wet the surface lightly with water spray, let dry and sand off the loose wood fibers. Remove the sanding dust.

Old and dirty surfaces or surfaces previously treated with, e.g. Supi Saunasuoja:

Wash with Supi Saunapesu cleaning agent according to instructions, rinse thoroughly and let dry. Sand and wipe the sanding dust off. If you leave traces of previous treatment substances under the wax, the end result will be more glossy than on untreated wood.

Not suitable for oiled (e.g. Supi Laudesuoja) wood surfaces unless the oil has worn away almost completely. Protect floors well before treatment as Supi Sauna Wax is absorbed easily into ceramic tile joints.

### Application

Stir Supi Sauna Wax thoroughly, also from time to time during use. Apply one coat of wax along the grain, not using more wax than the wood can absorb in a single application. Because the wax is very liquid, the most suitable application method is a foam brush or sponge. The surface will feel slippery if too much wax is applied.

You can try colored Supi Sauna Wax on a concealed spot to ensure that the color is right. The final color of the surface depends on the wood species. In order to achieve a uniform color, treat small surfaces in one continuous application and large panel surfaces 1–2 panels at a time.

Pre-heat and ventilate the sauna thoroughly before use.

Thermally modified wood surfaces should be treated with Supi Sauna Wax tinted to color TVT 318R.

### Cleaning of tools

Clean tools with water. Tikkurila Pensselipesu Tool Cleaner is recommended to remove slightly hardened paint.

### Maintenance instructions

If needed, no earlier than in approx. 1 month from surface treatment:

Clean the surface with Supi Saunapesu (mix 0.1–0.2 l of Saunapesu with 5 l of water).

### Environmental and waste disposal

Destroy liquid waste according to the local regulations for hazardous waste. Recycle empty, dry cans or dispose them of in accordance with local regulations.

### HEALTH AND SAFETY LABELLING according to Regulation (EC) No. 1272/2008

Contains 1,2-benzisothiazol-3(2H)-one (BIT) and reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)). May produce an allergic reaction. This product contains a biocidal product for the preservation of the product during storage. Contains C(M)IT/MIT (3:1). Wear protective gloves.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.